

POLYURETÁNY				
Farba	Materiál	Názov	Pracovná teplota	Tvrdosť
	TPU	Ecopur	-30° +110°C	Shore A 95 +/- 2
	TPU	H-Ecopur	-20° +110°C	Shore A 95 +/- 2
	CPU	G-Ecopur	-30° +110°C	Shore A 95 +/- 2
	TPU	T-Ecopur	-50° +110°C	Shore A 95 +/- 2
	TPU	S-Ecopur	-20° +110°C	Shore A 95 +/- 2
	TPU	X-Ecopur	-30° +110°C	Shore A 97 +/- 2
	TPU	XH-Ecopur	-20° +110°C	Shore A 97 +/- 2
	TPU	XS-Ecopur	-20° +110°C	Shore A 97 +/- 2
ELASTOMÉRY				
	NBR	ECORUBBER-1	-30°do +100°C	Shore A 85 +/- 5
	HNBR	ECORUBBER-H	-25°do +150°C	Shore A 85 +/- 5
	FPM,FKM	ECORUBBER-2	-20°do +200°C	Shore A 85 +/- 5
	EPDM	ECORUBBER-3	-50°do +150°C	Shore A 85 +/- 5
	MVQ	ECOSIL	-60°do +200°C	Shore A 85 +/- 5
	TFE/P	ECOFLAS	-10°do +200°C	Shore A 85 +/- 5
TERMOPLASTY				
	PTFE virgin	ECOFLON 1	-200°do +260°C	Shore D 57
	PTFE	ECOFLON 2 +25%GF+5%MoS ₂	-200°do +260°C	Shore D 60
	PTFE	ECOFLON 3 +40% bronze	-200°do +260°C	Shore D 64
	PTFE	ECOFLON 3F +40% bronze	-200°do +260°C	Shore D 64
	PTFE	ECOFLON 4 +25% Carbon	-200°do +260°C	Shore D 65
	PTFE	ECOFLON 5 modified	-200°do +260°C	Shore D 59
	PA	ECOMID	-40°do +100°C	Shore D 77
	POM	ECOTAL	-50°do +100°C	Shore D 82
	UHMWPE	ECOWEAR 1000	-200°do +90°C	Shore D 61
	PEEK	ECOPEAK	-60°do +256°C	Shore D 86
TERMOSEŤY				
		ECOTEX	-40°do +120°C	Shore D M98